

LACKIERPISTOLENEMPFEHLUNG ANEST IWATA

PRODUKT	CODE	WS 400		LS 400 entech	LPH 300	LPH 80	Impact AZ3
		BASE	CLEAR	HVLP	LVLP	LVLP Spot-Repair	HTE-S
Polyester Spritzspachtel	A712						2,5 1,6-2,0 bar
Wash Primer chromatfrei	D8092		1,3 2,0 bar				
Epoxy Grundierfüller	D8095		1,3-1,6 2,0 bar				1,6-1,8 1,5-1,8 bar
DP4000 2K Primer	D8501/5/7		1,3-1,4 2,0 bar				
DP5000 2K Primer	D8521/5/7				1,6-1,8 1,5-1,8 bar		1,6-1,8 1,5-1,8 bar
2K UHS Greymatic Füller	D8018/19/24				1,6-1,8 1,5-1,8 bar		1,6-1,8 1,5-1,8 bar
2K Rapid Greymatic	D8010/5/7				1,6-1,8 1,5-1,8 bar		1,6-1,8 1,5-1,8 bar
2K UHS Deltron Progress	D60XX		1,3 2,0 bar			1,2 1,2-1,6 bar	
ENVIROBASE High Performance	T40XX	1,3 HD 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,3 ETS 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,2 1,2-1,6 bar Nebelgang: 1,0-1,3 bar	
2K HS/UHS Klarlacke	D8130 D8135 D8140 D8141 D8171 D8173		1,3 2,0 bar			1,2 1,2-1,6 bar	
2K HS CeramicClear	D8122		1,3 2,0 bar			1,2 1,2-1,6 bar	
2K Matt-Lacksystem	D8115/17	1,3-1,5 2,0 bar		1,3-1,5 2,0 bar		1,2 1,2-1,6 bar	

LACKIERPISTOLENEMPFEHLUNG DEVILBISS

PRODUKT	CODE	GTI Pro		GTI Pro LITE		PRI Pro	SRI
		HVLP LK H1	Transtech LK T2	LK HV30	LK TE20	Transtech P1	HVLP LK 215
Polyester Spritzspachtel	A712					2,5 2,0-2,5 bar	
Wash Primer chromatfrei	D8092	1,2-1,3 2,0 bar	1,3 2,0-2,5 bar		1,3 2,0-2,5 bar		
Epoxy Grundierfüller	D8095		1,3-1,6 2,0-2,5 bar		1,3-1,6 2,0-2,5 bar		
DP4000 2K Primer	D8501/5/7		1,3-1,4 2,0-2,5 bar		1,3-1,4 2,0-2,5 bar		
DP5000 2K Primer	D8521/5/7					1,6-1,8 2,0-2,5 bar	
2K UHS Greymatic Füller	D8018/19/24					1,6-1,8 2,0-2,5 bar	
2K Rapid Greymatic	D8010/5/7					1,6-1,8 2,0-2,5 bar	
2K UHS Deltron Progress	D60XX		1,3-1,4 2,0-2,5 bar		1,3-1,4 2,0-2,5 bar		1,2 1,0-2,0 bar
ENVIROBASE High Performance	T40XX	1,2-1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,2-1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar			1,2 1,0-2,0 bar Nebelgang: 1,0-1,3 bar
2K HS/UHS Klarlacke	D8130 D8135 D8140 D8141 D8171 D8173		1,2 2,3-2,5 bar		1,2 2,3-2,5 bar		1,2 1,0-2,0 bar
2K HS CeramicClear	D8122		1,2 2,3-2,5 bar		1,2 2,3-2,5 bar		1,2 1,0-2,0 bar
2K Matt-Lacksystem	D8115/17	1,3-1,5 1,8 bar		1,3-1,5 1,8 bar			

LACKIERPISTOLENEMPFEHLUNG SATA

PRODUKT	CODE	SATAjet 5000 B		SATAjet 4000 B		SATAminijet 4400 B		SATAjet 100 BF	
		HVLP	RP	HVLP	RP	HVLP	RP	HVLP	RP
Polyester Spritzspachtel	A712								P 2,0 bar
Wash Primer chromatfrei	D8092	1,3 2,0 bar	1,4 2,0-2,2 bar	1,3 2,0 bar	1,4 2,0-2,2 bar				
Epoxy Grundierfüller	D8095		1,3-1,6 1,6-2,0 bar		1,3-1,6 1,6-2,0 bar				
DP4000 2K Primer	D8501/5/7		1,2-1,3 2,0-2,2 bar		1,2-1,3 2,0-2,2 bar				
DP5000 2K Primer	D8521/5/7							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K UHS Greymatic Füller	D8018/19/24							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K Rapid Greymatic	D8010/5/7							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K UHS Deltron Progress	D60XX		1,2-1,3 2,0-2,2 bar		1,2-1,3 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
ENVIROBASE High Performance	T40XX	1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar			
2K HS/UHS Klarlacke	D8130 D8135 D8140 D8141 D8171 D8173		1,2 2,0-2,2 bar		1,2 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
2K HS CeramicClear	D8122		1,2 2,0-2,2 bar		1,2 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
2K Matt-Lacksystem	D8115/17	1,3-1,5 1,8 -2,0 bar		1,3-1,5 1,8 - 2,0 bar					