

LACKIERPISTOLENEMPFEHLUNG ANEST IWATA

PRODUKT	CODE	WS-400 evo clear	W-400 WBX	LS-400 entech	LPH-300	W-300 WB	LPH-80	AZ3 HTE2
		Compliant		HVLP	Füller	Smart Repair	Spot-Repair	HVLP
Polyester Spritzspachtel	A712							2,5 2,0 bar
Wash Primer chromatfrei	D8092	1,3 HD 2,0 bar	1,3 2,0 bar					
Epoxy Grundierfüller	D8095	1,4-1,5 HD 2,0 bar						
DP4000 2K Primer	D8501/5/7	1,3-1,4 HD 2,0 bar	1,4 2,0 bar					
DP5000 2K Primer	D8521/5/7				1,8 1,0-1,5 bar			
DP6000 Rapid Primer	D8531/5/7				1,6-1,8 1,0-1,5 bar			
2K UHS Greymatic Füller	D8018/19/24				1,6-1,8 1,0-1,5 bar			
2K Rapid Greymatic	D8010/5/7				1,8 1,0-1,5 bar			
2K UHS Deltron Progress	D60XX	1,3 HD 1,8-2,0 bar	1,3-1,4 2,0 bar				1,2 1,0-1,2 bar	
ENVIROBASE High Performance	T40XX			1,3 ETS 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,2 1,5 bar	1,2 1,0-1,2 bar Nebelgang: 0,8-1,0 bar	
2K HS/UHS Klarlacke	D8130 D8135 D8140 D8141 D8173 D8175 D8176	1,3 HD 1,8-2,0 bar	1,3-1,4 2,0 bar			1,2 1,5 bar	1,2 1,0-1,2 bar	
2K HS CeramicClear	D8122	1,3 HD 2,0 bar					1,2 1,0-1,2 bar	
2K Matt-Lacksystem	D8115/17			1,3-1,5 ETS 1,8 bar			1,2 1,0-1,2 bar	

* Angaben in **fett/bold**: = primäre Empfehlung

LACKIERPISTOLENEMPFEHLUNG DEVILBISS

PRODUKT	CODE	GTI Pro		GTI Pro LITE		PRI Pro LITE	SRI Pro LITE	
		HVLP HV30	Transtech TE20	HVLP LK HV30	Transtech LK TE20	Transtech PR10	HVLP HV5	Transtech TE5
Polyester Spritzspachtel	A712					2,5 2,0-2,5 bar		
Wash Primer chromatfrei	D8092	1,2-1,3 2,0 bar	1,3 2,0 bar		1,3 2,0 bar			
Epoxy Grundierfüller	D8095		1,3-1,6 2,0 bar		1,3-1,6 2,0 bar			
DP4000 2K Primer	D8501/5/7		1,3-1,4 2,0 bar		1,3-1,4 2,0 bar			
DP5000 2K Primer	D8521/5/7					1,6-1,8 2,0-2,5 bar		
DP6000 Rapid Primer	D8531/5/7					1,6-1,8 2,0-2,5 bar		
2K UHS Greymatic Füller	D8018/19/24					1,6-1,8 2,0-2,5 bar		
2K Rapid Greymatic	D8010/5/7					1,6-1,8 2,0-2,5 bar		
2K UHS Deltron Progress	D60XX		1,3-1,4 2,0 bar		1,3-1,4 2,0 bar		1,2-1,4 1,0-2,0 bar	1,2-1,4 1,0-2,0 bar
ENVIROBASE High Performance	T40XX	1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar			1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar	1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar
2K HS/UHS Klarlacke	D8130 D8135 D8140 D8141 D8173 D8175 D8176		1,2-1,3 2,3-2,5 bar		1,2-1,3 2,0 bar		1,2-1,4 1,0-2,0 bar	1,2-1,4 1,0-2,0 bar
2K HS CeramicClear	D8122		1,2-1,3 2,3-2,5 bar		1,2-1,3 2,0 bar		1,2-1,4 1,0-2,0 bar	1,2-1,4 1,0-2,0 bar
2K Matt-Lacksystem	D8115/17	1,4 1,8 bar		1,4 1,8 bar				

LACKIERPISTOLENEMPFEHLUNG SATA

PRODUKT	CODE	SATAjet 5000 B		SATAjet 4000 B		SATAminijet 4400 B		SATAjet 100 BF	
		HVLP	RP	HVLP	RP	HVLP	RP	HVLP	RP
Polyester Spritzspachtel	A712								P 2,0 bar
Wash Primer chromatfrei	D8092	1,3 2,0 bar	1,4 2,0-2,2 bar	1,3 2,0 bar	1,4 2,0-2,2 bar				
Epoxy Grundierfüller	D8095		1,3-1,6 1,6-2,0 bar		1,3-1,6 1,6-2,0 bar				
DP4000 2K Primer	D8501/5/7		1,2-1,3 2,0-2,2 bar		1,2-1,3 2,0-2,2 bar				
DP5000 2K Primer	D8521/5/7							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
DP6000 Rapid Primer	D8531/5/7							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K UHS Greymatic Füller	D8018/19/24							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K Rapid Greymatic	D8010/5/7							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K UHS Deltron Progress	D60XX		1,2-1,3 2,0-2,2 bar		1,2-1,3 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
ENVIROBASE High Performance	T40XX	1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar			
2K HS/UHS Klarlacke	D8130 D8135 D8140 D8141 D8173 D8176		1,2 2,0-2,2 bar		1,2 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
	D8175		1,1-1,2 2,0-2,2 bar		1,2 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
2K HS CeramicClear	D8122		1,2 2,0-2,2 bar		1,2 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
2K Matt-Lacksystem	D8115/17	1,3-1,5 1,8 -2,0 bar		1,3-1,5 1,8 - 2,0 bar					