

LACKIERPISTOLENEMPFEHLUNG ANEST IWATA

PRODUKT	CODE	WS 400 evo clear	W-400 WBX	LS-400 entech	LPH-300	W-300 WB	LPH-80	AZ3 HTE2
		Compliant		HVLP	Füller	Smart Repair	Spot-Repair	HVLP
Polyester Spritzspachtel	A712							2,5 2,0 bar
Wash Primer chromatfrei	D8092	1,3 HD 2,0 bar	1,3 2,0 bar					
Epoxy Grundierfüller	D8595	1,4-1,5 HD 2,0 bar						
DP4000 2K Primer	D8501/5/7	1,3-1,4 HD 2,0 bar	1,4 2,0 bar					
DP5000 2K Primer	D8521/5/7				1,8 1,0-1,5 bar			
DP6000 Rapid Primer	D8531/5/7				1,6-1,8 1,0-1,5 bar			
2K UHS Greymatic Füller	D8018/19/24				1,6-1,8 1,0-1,5 bar			
2K Rapid Greymatic	D8010/5/7				1,8 1,0-1,5 bar			
2K UHS Deltron Progress	D60XX	1,3-1,4 HD 1,8-2,0 bar	1,3-1,4 2,0 bar				1,2 1,0-1,2 bar	
ENVIROBASE High Performance	T40XX			1,3 ETS 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,2 1,5 bar	1,2 1,0-1,2 bar Nebelgang: 0,8-1,0 bar	
2K HS/UHS Klarlacke	D8130 D8135 D8141 D8173 D8175 D8176	1,3 HD 1,8-2,0 bar	1,3-1,4 2,0 bar			1,2 1,5 bar	1,2 1,0-1,2 bar	
2K HS CeramicClear	D8122	1,3 HD 2,0 bar					1,2 1,0-1,2 bar	
2K Matt-Lacksystem	D8115/17			1,3-1,5 ETS 1,8 bar			1,2 1,0-1,2 bar	

* Angaben in **fett/bold**: = primäre Empfehlung

LACKIERPISTOLENEMPFEHLUNG DEVILBISS

PRODUKT	CODE	GTI Pro		GTI Pro LITE		DV1-B	PRI Pro LITE	SRI Pro LITE	
		HVLP HV30	Transtech TE20	HVLP LK HV30	Transtech LK TE20	HVLP / Plus	Transtech PR10	HVLP HV5	Transtech TE5
Polyester Spritzspachtel	A712						2,5 2,0-2,5 bar		
Wash Primer chromatfrei	D8092	1,2-1,3 2,0 bar	1,3 2,0 bar		1,3 2,0 bar				
Epoxy Grundierfüller	D8595		1,3-1,6 2,0 bar		1,3-1,6 2,0 bar				
DP4000 2K Primer	D8501/5/7		1,3-1,4 2,0 bar		1,3-1,4 2,0 bar				
DP5000 2K Primer	D8521/5/7						1,6-1,8 2,0-2,5 bar		
DP6000 Rapid Primer	D8531/5/7						1,6-1,8 2,0-2,5 bar		
2K UHS Greymatic Füller	D8018/19/24						1,6-1,8 2,0-2,5 bar		
2K Rapid Greymatic	D8010/5/7						1,6-1,8 2,0-2,5 bar		
2K UHS Deltron Progress	D60XX		1,3-1,4 2,0 bar		1,3-1,4 2,0 bar			1,2-1,4 1,0-2,0 bar	1,2-1,4 1,0-2,0 bar
ENVIROBASE High Performance	T40XX	1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,2B 1,8bar Nebelgang: 1,4bar /Silber grob 1,2bar		1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar	1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar
2K HS/UHS Klarlacke	D8130 D8135 D8141 D8173 D8175 D8176		1,2-1,3 2,3-2,5 bar		1,2-1,3 2,0 bar			1,2-1,4 1,0-2,0 bar	1,2-1,4 1,0-2,0 bar
2K HS CeramicClear	D8122		1,2-1,3 2,3-2,5 bar		1,2-1,3 2,0 bar			1,2-1,4 1,0-2,0 bar	1,2-1,4 1,0-2,0 bar
2K Matt-Lacksystem	D8115/17	1,4 1,8 bar		1,4 1,8 bar					

LACKIERPISTOLENEMPFEHLUNG SATA

PRODUKT	CODE	SATAjet 5000 B		SATAjet X 5500		SATAminijet 4400 B		SATAjet 100 BF	
		HVLP	RP	HVLP	RP	HVLP	RP	HVLP	RP
Polyester Spritzspachtel	A712								P 2,0 bar
Wash Primer chromatfrei	D8092	1,3 2,0 bar	1,4 2,0-2,2 bar	O Düse 1,3 2,0 bar	I Düse 1,4 2,0-2,2 bar				
Epoxy Grundierfüller	D8595		1,3-1,6 1,6-2,0 bar		I Düse 1,3-1,6 1,6-2,0 bar				
DP4000 2K Primer	D8501/5/7		1,2-1,3 2,0-2,2 bar		I Düse 1,2-1,3 2,0-2,2 bar				
DP5000 2K Primer	D8521/5/7							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
DP6000 Rapid Primer	D8531/5/7							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K UHS Greymatic Füller	D8018/19/24							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K Rapid Greymatic	D8010/5/7							1,6-1,8 2,0 bar	1,6-1,8 2,0 bar
2K UHS Deltron Progress	D60XX		1,2-1,3 2,0-2,2 bar		I Düse 1,2-1,3 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
ENVIROBASE High Performance	T40XX	1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		O Düse 1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar		1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar			
2K HS/UHS Klarlacke	D8130 D8135 D8140 D8141 D8173 D8176		1,2 2,0-2,2 bar		I Düse 1,2 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
	D8175		1,1-1,2 2,0-2,2 bar		I Düse 1,2 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
2K HS CeramicClear	D8122		1,2 2,0-2,2 bar		I Düse 1,2 2,0-2,2 bar		1,0-1,2 1,0-2,0 bar		
2K Matt-Lacksystem	D8115/17	1,3-1,5 1,8 -2,0 bar		I Düse 1,3-1,5 1,8 - 2,0 bar					